

Technical Data Sheet

QGel 300 High Strength Silicone Gel

PRODUCT DESCRIPTION

QGel 300 is a clear, very soft, tough, moderately cross-linked silicone polymer. Silicone gels are used to provide protection from vibration, thermal or mechanical shock. Silicone gels also provide excellent moisture protection.

KEY FEATURES

- Soft, with considerably higher strength than general purpose gels
- One to one mix ratio
- 24-hour room temperature cure
- Dispensing equipment not necessary

TYPICAL PROPERTIES

UNCATALYZED		
TEST	QGel 300 A	QGel 300 B
Appearance	Transparent	Transparent
Viscosity	1,000 cps	2,000 cps
Specific Gravity	0.97	0.97

CATALYZED	
MIX RATIO 1:1	
TEST	RESULT
Gel Time at 25 °C *	135 minutes

* Gel time is defined as the time required for the material to become a solid or a semi-solid.

CURED PROPERTIES	
Cure Profile	30 minutes at 150 °C
	60 minutes at 100 °C
	20 hours at 25 °C
Penetration, 30 minutes at 150 °C	5 – 9 mm

ELECTRICAL PROPERTIES	
Dielectric Strength	499 V/mil
	19.6 kV/mm

Technical Data Sheet

ADDITIONAL PROPERTIES	
Service Temperature Range	-55 °C – 204 °C
Adhesion	Excellent adhesion to glass, copper and to select other substrates

MIXING

QGel 300 should be thoroughly mixed using a 1:1 ratio by weight. Once the components are mixed, the curing process begins. The gel time of the mixed material is listed above under typical properties. Fast curing gels (less than 30-minute gel-time) should be dispensed utilizing automated mix and dispense equipment.

DE-AERATION

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.

STORAGE AND SHELF LIFE

This product is best when used within 24 months from date of manufacture. See product label and/or CoA for specific "Use By Date".

Product should be stored in its original, unopened container in an environment that does not exceed 38 °C (100 °F).

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

DISCLAIMER

The technical data listed is provided for reference only and is not intended as product specifications. CHT USA's team accepts opportunities to either modify specifications in a current product or custom formulate a new one to meet your requirements. For sales and technical assistance, please contact us at: **(804) 271-9010** or **1-800-852-3147**.

Please be sure to visit our website daily for our complete product portfolio, new product introductions and more:

www.silicone-experts.cht.com

www.quantumsilicones.com

CHT USA - Richmond, 7820 Whitepine Road, Richmond, VA 23237

Manufacturing and R&D Facility, 8021 Reycan Road, Richmond, VA 23237